



M|B|I
M. BRASHEM, INC.

14023 NE 8th Street
Bellevue, WA 98007, USA
Phone: 1-425-641-1566
Toll Free: 1-800-274-2008
Fax: 1-425-641-1583
E-mail: info@mbigraphite.com

Quality Engineered Graphite
Technical Bulletin

GRADE MBIS-L8

Is a quality, fine grain, high strength isostatically molded graphite that can be machined to tight tolerances and used in a vast array of the most difficult applications.

TYPICAL APPLICATIONS INCLUDE:

Continuous casting dies, semiconductor and composite parts, sintering (ceramic and electronic), hot pressing, diamond drill bits and rocket nozzles.

SIZES

Available upon request.

TYPICAL PROPERTIES @ ROOM TEMPERATURE (ENGLISH)

Bulk Density (g/cm ³)	1.80
Average Particle Size (in.)	.001
Specific Resistance (10 ⁻⁴ Ω.in)	5.91
Flexural Strength (psi)	5,814
CTE (10 ⁻⁶ /°F)	2.5
Ash Content (%/nppm)	.07/700
Young's Modulus (x10 ⁻⁶ /psi)	1.7
Compressive Strength (psi)	12,501
Hardness (shore)	50

*Note: This information is not a warranty. It is offered solely for your consideration, investigation and verification.

"GRAPHITE IS OUR SPECIALTY"

Phone: 1-800-274-2008

www.mbigraphite.com

Fax: 1-425-641-1583